



NOTE: BACK POSTS MAYBE DELETED IF WITHIN 4' OF FENCE, BUILDING OR OTHER PHYSICAL BARRIER.



COATING REQUIREMENT:
 APPLY TWO COATS (2 - 4 MILS DFT EA) OF YELLOW ALKYD ENAMEL OVER ONE COAT OF GRAY RUST-INHIBITING ALKYD PRIMER (2 - 4 MILS DFT). COLOR SHALL BE PER THE STANDARD HIGHWAY COLOR CODE OF THE MUTCD.

GUARD POST DETAIL

REF SECTION 312 OF 2006 INTERNATIONAL FIRE CODE